

# TECHNICAL DATA SHEET NYLON

Brand: Fiberlogy

Name: Fiberlogy Nylon PA12

Manufacturer: Fiberlab S.A., Brzezie 387, 32-014 Brzezie, Poland

Description: Nylon filament designed for printing in FFF/FDM technology, available in two

different colors, wound on a spool, vacuum-packed in plastic, placed in a

cardboard box.

#### Technical information

Diameter: 1,75 mm

Diameter Tolerance: +/- 0,02 mm

Avg Roundness: + 0,01 mm

Net Weight: 0,85 kg

Print Temperature: 255°C - 270°C

Bed Temperature: ~100°C

### **Material Properties**

Mechanical Properties	Test Method	Unit	Typical Value
Tensile modulus	ISO 527	MPa	1400
Tensile strength at break	ISO 527	MPa	51
Flexural modulus	ISO 178	MPa	1200
Density	ISO 483	g/cc	1.02
Rheological Properties	Test Method	Unit	Typical Value
MVI (235 °C / 5 kg)	ISO 11 357	Cm <sup>3</sup> /10min	180
Thermal Properties	Test Method	Unit	Typical Value
Melting point	ISO 1133	°C	180

### Recommended print settings



# TECHNICAL DATA SHEET NYLON

Settings	Unit	Value
Printing temperature	°C	255 - 270
Bed temperature <sup>1</sup>	°C	~100

<sup>1</sup> If using plates or other means to increase the adhesion, the heating of the bed is not required.

Informations set forth herein has been gathered from standard reference materials and/or supplier test data. To the best knowledge and belief of Fiberlab S.A. they are accurate and reliable. Information is offered only for your consideration, investigation and verification. Fiberlab S.A. makes no warranties, expressed or implied, with respect to the use of such information or the use of the specific material identified herein combination with any other material or process, and assumes no responsibility therefore.

Last update: 23 May 2018